

Technical Data Sheet

Cured Properties

Properties	Standard	Units	PU 3670 (Unfilled)	PU 3670 (200% A91)
Hardness	BS EN ISO 868	Shore D	75 – 80	80 – 85
Linear Shrinkage	500 x 50 x10 mm	%	< 0.05	< 0.05
Tensile Strength	BS EN ISO 527	MPa	18 – 22	7 – 12
Elongation at Break	BS EN ISO 527	%	2 – 4	2 – 4
Flexural Strength	BS EN ISO 178	MPa	30 – 40	20 – 30
Flexural Modulus	BS EN ISO 178	MPa	800 – 1300	2200 – 2500
Heat Distortion Temperature (HDT)	TMA	°C	62 – 67	67 – 72
Glass Transition Temperature (Tg)	DMA	°C	93 – 99	93 – 99

Method of Use

Mould Preparation

Ensure that the mould is clean and dry and if the mould is made from metal, wood or resin, use a release agent such as R7. For flexible moulds, use Alchemix RTV silicone rubber. If the mould is wooden, ensure the wood is well sealed with varnish and/or wax based release agents such as R7.

Resin Preparation

Shake the Part A can thoroughly in order to homogenise the resin. For best results, ensure that the two components are at 20 – 25°C before mixing.

Mixing Instructions

When using unfilled, add the correct amount of Part B to the Part A and stir for 30 seconds. Pour carefully in one place into the mould in order to avoid air inclusion.

If using filled, we recommend the use up to 200% filler. Use Alchemix A91 Aluminium Trihydroxide for general bulking out and shrinkage reduction, or Alchemix A83 Aluminium Powder for higher temperature applications. Large quantities of material, filled or unfilled, will always produce more exotherm and will gel quicker than smaller amounts.

Technical Data Sheet

If aiming to use 200% filler in a 200g mix, weigh out 100g of part A and mix in 200g filler. Then weigh out 100g of B and mix in 200g filler. Then mix the two components.

Curing

The casting can generally be demoulded in 15 – 40 minutes at room temperature. The precise demould time will vary with casting thickness, as thin section units will cure slower than thicker section units. When casting thin wall sections, ensure that the mould and resins are at least 20 – 25°C to facilitate a good cure and reduce the risk of brittleness. To reduce the cure time, the mould can be pre-warmed to 40 – 60°C. It is not recommended to heat the liquid components.

Storage

ALCHEMIX PU 3670A and B should be stored in original, unopened containers between 20 and 25°C. ALCHEMIX PU 3670B may crystallise partially or completely if not stored at above 20°C. Like all polyurethanes, both components are moisture sensitive. Moisture absorption will cause excessive aeration in cast parts. KEEP THE PACKING TIGHTLY SEALED WHEN NOT IN USE.

If stored under the above conditions, ALCHEMIX PU 3670A and B will have a shelf life of 6 months, from the date of production.

Packaging

ALCHEMIX PU 3670A is supplied in 1kg, 5kg and 25kg containers.
ALCHEMIX PU 3670B is supplied in 1kg, 5kg and 25kg containers.

(Please contact Alchemie Ltd for bulk supply)

Technical Data Sheet

Further Information

All data listed relates to typical values. This data should not be considered a product specification.

Our technical advice, whether verbal, or in writing is given in good faith, but without warranty – this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended process and use.

Before using any of our products, users should familiarise themselves with the relevant Technical and MSDS provided by Alchemie Ltd.

Alchemie Limited

Alchemie Ltd develop, formulate and distribute Epoxy Resins, Polyurethane Resins, Silicones, Model Boards and Sheet Wax for use in the following applications:

- Electrical encapsulation
- Rapid Prototyping
- Prototypes
- Casting
- Gel Coating
- Laminating
- Model Making
- Master Models
- Flexible and rigid mould making

We offer fast service, technical support, development expertise, innovative products, diverse knowledge and experience.

We are a well-established company, with a high level of investment and experience. We implement BS EN ISO 9001.

Alchemie® and Alchemix® are registered Trademarks of Alchemie Ltd, Warwick Road, Kineton, Warwick, England, CV35 0HU, England, United Kingdom. Ph: +44 (0)1926 641600; FAX: +44 (0)1926 641698